



*Institute of Paper Science and Technology
Atlanta, Georgia*

IPST Technical Paper Series Number 844

Lignin Structure in a Mutant Pine Deficient in Cinnamyl Alcohol Dehydrogenase

C. Lapierre, B. Pollet, J.J. MacKay, R.R. Sederoff

March 2000

Submitted to
Journal of Agricultural and Food Chemistry

Copyright© 2000 by the Institute of Paper Science and Technology

For Members Only

INSTITUTE OF PAPER SCIENCE AND TECHNOLOGY PURPOSE AND MISSIONS

The Institute of Paper Science and Technology is an independent graduate school, research organization, and information center for science and technology mainly concerned with manufacture and uses of pulp, paper, paperboard, and other forest products and byproducts. Established in 1929 as the Institute of Paper Chemistry, the Institute provides research and information services to the wood, fiber, and allied industries in a unique partnership between education and business. The Institute is supported by 51 North American companies. The purpose of the Institute is fulfilled through four missions, which are:

- to provide multidisciplinary graduate education to students who advance the science and technology of the industry and who rise into leadership positions within the industry;
- to conduct and foster research that creates knowledge to satisfy the technological needs of the industry;
- to provide the information, expertise, and interactive learning that enables customers to improve job knowledge and business performance;
- to aggressively seek out technological opportunities and facilitate the transfer and implementation of those technologies in collaboration with industry partners.

ACCREDITATION

The Institute of Paper Science and Technology is accredited by the Commission on Colleges of the Southern Association of Colleges and Schools to award the Master of Science and Doctor of Philosophy degrees.

NOTICE AND DISCLAIMER

The Institute of Paper Science and Technology (IPST) has provided a high standard of professional service and has put forth its best efforts within the time and funds available for this project. The information and conclusions are advisory and are intended only for internal use by any company who may receive this report. Each company must decide for itself the best approach to solving any problems it may have and how, or whether, this reported information should be considered in its approach.

IPST does not recommend particular products, procedures, materials, or service. These are included only in the interest of completeness within a laboratory context and budgetary constraint. Actual products, materials, and services used may differ and are peculiar to the operations of each company.

In no event shall IPST or its employees and agents have any obligation or liability for damages including, but not limited to, consequential damages arising out of or in connection with any company's use of or inability to use the reported information. IPST provides no warranty or guaranty of results.

The Institute of Paper Science and Technology assures equal opportunity to all qualified persons without regard to race, color, religion, sex, national origin, age, disability, marital status, or Vietnam era veterans status in the admission to, participation in, treatment of, or employment in the programs and activities which the Institute operates.

**LIGNIN STRUCTURE IN A MUTANT PINE DEFICIENT
IN CINNAMYL ALCOHOL DEHYDROGENASE**

Author for correspondence :

John MacKay

Institute of Paper Science and Technology

500 10th Street N.W.

Atlanta, GA 30318 (USA)

email john.mackay@ipst.edu

Phone 404-894-0363

Fax 404-894-4778

**LIGNIN STRUCTURE IN A MUTANT PINE DEFICIENT
IN CINNAMYL ALCOHOL DEHYDROGENASE**

Catherine Lapierre¹, Brigitte Pollet¹, John J. MacKay², Ronald R. Sederoff³

¹Laboratoire de Chimie Biologique INRA, Institut National Agronomique, 78850 Thiverval-

Grignon, France. E-mail : lapierre@platon.grignon.inra.fr

²Institute of Paper Science and Technology, 500 10th Street N.W., Atlanta, GA 30318, USA

³Forest Biotechnology Group, Box 8008, North Carolina State University, NC 27695, USA

ABSTRACT

Cinnamyl alcohol dehydrogenase (CAD) activity is deficient in loblolly pine (*Pinus taeda* L.), harboring a mutated allele of the *cad* gene (*cad-nl*). We compared lignin structure of CAD-deficient and wild type pines, both types segregating within full-sib families obtained by controlled crosses. The type and frequency of lignin building units and distribution of interunit bonds were determined from the GC-MS analysis of thioacidolysis monomers and dimers. While the lignin content was only slightly reduced, the lignin structure was dramatically modified by the mutation in both mature and juvenile trees. Lignins from CAD-deficient pine displayed unusually high levels of coniferaldehyde and dihydroconiferyl alcohol (DHCA). In addition, biphenyl and biphenyl ether bonds were in large excess in these abnormal lignins. These results suggest that the CAD-deficient pines efficiently compensate for the shortage in normal lignin precursors by utilizing non traditional wall phenolics to construct unusual lignins particularly enriched in resistant interunit bonds.

Keywords. Lignification; altered lignin structure; pine (*Pinus taeda* L.); Thioacidolysis, dihydroconiferyl alcohol.

INTRODUCTION

Lignins are cell wall polymers essential for mechanical support, water transport, and disease resistance in vascular terrestrial plants. In wood, lignins are particularly abundant, they typically account for 20 to 30% of the dry weight. Removal of lignin from wood is the basis of kraft pulping, the major chemical process used for the production of high quality pulp and paper. In recent years, studies of mutant and transgenic plants with altered monolignol biosynthesis have suggested that plants have a high level of metabolic plasticity in the formation of lignin (Whetten *et al.*, 1998; Boudet, 1998). This means that unusual phenolics may be committed to the formation of lignins when there is a metabolic shortage in one of the *p*-hydroxycinnamyl alcohols, namely, *p*-coumaryl, coniferyl and sinapyl alcohol, the conventional monolignols involved in the lignin polymerization step. For example, a depressed caffeic acid *O*-methyltransferase (COMT) activity significantly increases the incorporation of 5-hydroxyconiferyl alcohol in angiosperm lignins (Lapierre *et al.*, 1988; van Doorselaere *et al.*, 1995) while a reduction in cinnamyl alcohol dehydrogenase (CAD) and in cinnamyl-CoA reductase (CCR), respectively, increases the incorporation of cinnamaldehyde (Halpin *et al.*, 1994; Hibino *et al.*, 1995) and tyramine ferulate (Ralph *et al.*, 1998). In addition, naturally occurring variation in lignin subunit composition that exists among diverse plant taxa happens to extend beyond the three traditional *p*-hydroxycinnamyl alcohols, again highlighting the ability of plants to adapt to diverse changes in lignin precursor supply. For example, grass lignins incorporate *p*-coumarate and ferulate units (Ralph *et al.*, 1994; Jacquet *et al.*, 1995). Thus, there is growing evidence that the structure of the polymers we call lignins may be dictated by precursor supply and variations therein (Sederoff *et al.*, 1999).

Recently, a mutant loblolly pine (*Pinus taeda* L.) was discovered in which the expression of the gene encoding cinnamyl alcohol dehydrogenase (CAD; EC 1.1.1.195) is severely reduced due to the presence of a recessive (*cad-n1*) allele (MacKay *et al.*, 1997). In the xylem of homozygous mutant seedlings, CAD activity was almost completely deficient (between 0 and 1% of wild type), while lignin content was only slightly decreased (MacKay *et al.*, 1997). NMR analysis of an isolated milled wood lignin sample revealed the incorporation of high levels of coniferaldehyde, of dihydroconiferyl alcohol (DHCA) and vanillin in the CAD-deficient pine (Ralph *et al.*, 1997). The finding that DHCA was utilized as a major lignin precursor is very significant. However, it was based upon NMR analysis of lignin isolated from a single CAD-deficient tree and was not quantitative. This finding thus needs to be verified and confirmed in several specimens, preferably with a method that does not rely on lignin isolation. In this paper, we report on the quantitative evaluation of the lignin in several wild type and mutant seedlings or mature trees to further delineate the specific structural traits associated with CAD deficiency in gymnosperm lignin. This evaluation was based on the GC-MS analysis of lignin-derived monomers and dimers released upon thioacidolysis.

MATERIALS AND METHODS

Plant Material. Loblolly pine seedlings of a selfed family from a *cad-n1* heterozygous mother-tree (7-56) were grown for 10 months under standard greenhouse conditions and then the *cad* genotype of each one was determined using RAPD markers as a finger-printing method (MacKay *et al.*, 1997). Five wild type and four homozygous *cad-n1* seedlings were randomly selected for this study (Figure 1). Identification and characterization of two 12-year-old trees, one mutant (28% lignin) and one wild type (29.5% lignin) were also described previously

(Ralph *et al.*, 1997; MacKay *et al.*, 1999). In addition, one mutant tree (27.4% lignin) was selected from a 2-year-old field planting of a selfed family from the mother-tree 7-56 (L. Pearson, Westvaco). Wild type and mutant wood samples from 10-month-old seedlings and from 12- or 2-year-old trees were ground before successive solvent extractions (toluene-ethanol, 2/1, v/v; ethanol and water). The lignin content of these seedlings and other trees was determined on the dry extract-free wood and by the Klason method according to standard procedure (MacKay *et al.*, 1997).

Analysis by Thioacidolysis. The determination of the lignin-derived monomers and dimers released by thioacidolysis of extract-free wood was done according to the standard procedure (Lapierre *et al.*, 1999). These compounds were systematically identified by GC-MS of their trimethylsilylated (TMS) derivatives. The GC-FID and GC-MS quantitative evaluation of dihydroconiferyl alcohol was run by reference to a calibration carried out with the authentic compound. This authentic compound was obtained by Raney nickel reduction of commercial coniferyl alcohol. Thioacidolyses were run in duplicate. Standard errors between duplicate analyses were in the 3-5% range for the lignin-derived monomers and in the 5-10% range for the lignin-derived dimers.

RESULTS

Total Yield and Relative Distribution of Thioacidolysis Monomers. Analysis of lignin structure in extract-free wood of CAD-deficient and normal pine was performed by thioacidolysis. The key reaction of thioacidolysis (lignin depolymerization using BF_3 etherate in ethanethiol-dioxane mixture) is the specific cleavage of lignin β -O-4 ether bonds (Lapierre,

1993; Lapierre *et al.*, 1995). On this basis, the total yield in lignin-derived monomers is a close reflection of the lignin content in units only involved in β -O-4 bonds. In pine and other softwoods, thioacidolysis specifically releases phenolic monomers comprised of guaiacyl (G) G-CHR-CHR-CH₂R (R = SEt) as the major compounds (erythro and threo isomers), together with a series of other lignin-derived phenolics (discussed in the following section). From the total yield in lignin-derived monomers (Table 1), we calculated the percentage of lignin units in β -O-4 bonds based upon two assumptions: 1) that the recovery yield of these monomers is about 80% (including both the reaction and the extraction yields from model compound experiments), and 2) that the average molecular weight of the basic C₃C₆ unit is 180.

The total yield in lignin-derived monomers emphasizes a dramatic alteration of lignin profiles in mutant pine seedlings and mature tree relative to wild type samples (Table 1). Lignin units only involved in β -O-4 bonds are three times less abundant in mutant samples (7-8% versus 21-25% in wild type). Conversely, this result strongly supports the hypothesis that resistant carbon-carbon bonds are unusually abundant in mutant lignins - more than 90% of phenylpropane units are involved in such condensed bonds, versus the conventional 75% level observed for the normal gymnosperm lignin. This remarkably high condensation degree of the mutant lignin was consistent in all the samples but was slightly more pronounced in pine seedlings than in the older trees.

The relative distribution of the main lignin-derived monomers was severely affected by the *cad-nl* allele. Monomers diagnostic for the β -O-4 linked structures coniferaldehyde, vanillin and DHCA were released in low proportion from the wild type samples, but recovered in large relative amounts from extract-free mutant samples (Figure 2). In a previous study, lignin was

isolated from one normal and one *cad-n1* mutant 12-year-old tree, the same trees as used here (Ralph *et al.*, 1997). Upon NMR analysis of soluble lignin samples isolated with a 12-17% yield relative to the total lignin amount, it was shown that the lignin subunits coniferaldehyde, vanillin and dihydroconiferyl alcohol were increased in the CAD-deficient pine, with DHCA signals increasing the most. Increased incorporation of aromatic aldehyde (e.g. coniferaldehyde and vanillin) and decreased coniferyl content were also clearly supported by FTIR analysis extractive-free wood samples from the same trees (MacKay *et al.*, 1997; MacKay *et al.*, 1999). FTIR spectra did not appear to be diagnostic for DHCA. Thioacidolysis quantitatively confirmed the altered subunit composition in the native lignins of mature trees, analyzed *in situ* without any isolation step. Data obtained for the 10-month-old seedlings revealed that the increased incorporation of coniferaldehyde and DHCA occurred at early developmental stages and was more pronounced in juvenile seedlings relative to 12-year-old trees. Thus, it is clearly established that the increased incorporation of DHCA and coniferaldehyde is indeed specifically linked to the homozygous *cad-n1* genotype.

In addition, we observed that the ratio of *p*-hydroxyphenyl to guaiacyl thioacidolysis monomers (H/G ratio, Table 2) was systematically higher in the mutant samples relative to wild type ones, with some values (*S*₅ and 2-year-old tree) similar to the levels characteristic of compression wood lignins (Table 2). With the reservation that this H/G ratio does not reveal the trend for H units in the whole polymer but only in β -O-4 linked lignin structures, this result suggests an increased incorporation of H units with conventional lignin side chain in the mutant lignin. On this basis and in agreement with NMR results (Ralph *et al.*, 1997), it seems that the mutation does not affect the formation of *p*-coumaryl alcohol, the precursor of H units. Taken

together, these results show that lignin units usually present in relatively minor amounts in gymnosperms (namely coniferaldehyde, vanillin, DHCA and H units) have been extensively incorporated into the lignin of the mutant pine. The incorporation of these monomers provides a mechanism to compensate for the shortage in coniferyl alcohol, the traditional precursor of conifer lignins.

Thioacidolysis of pre-methylated samples is an effective method of determining free phenolic groups in lignin samples (Lapierre *et al.*, 1995). This method was applied with wood samples from the normal and CAD-deficient pine. The proportion of free phenolic groups within the β -O-4 linked lignin moiety was twofold higher in the lignin of 12-year-old CAD-deficient tree (38% of β -O-4 G units were free phenolic) relative to the analogous wild type sample (17%). Such an increase in free phenolic groups was also reported in the lignins of CAD down-regulated poplar trees, which made them more amenable to kraft delignification (Lapierre *et al.*, 1999). This increase may originate from a higher crosslinking degree or from a lower average molecular weight of the native lignin polymers. The latter hypothesis is supported by gel permeation chromatography of isolated lignins (Dimmel *et al.*, 1999). It, therefore, seems that CAD deficiency induces important alterations of native lignins not only at the chemical, but also at the macromolecular level.

Distribution of Lignin Resistant Interunit Bonds Revealed by the Analysis of Lignin-derived Dimers. The GC-MS analysis of lignin-derived dimers released after thioacidolysis and desulfurization further pointed at the unusual structural traits of the lignin in mutant pine samples. Many of the various dimers recovered from mutant samples (Figure 3) were original structures characterized herein for the first time.

Dimers **3**, **11**, **16**, and **17**, which are representatives of conventional 5-5, 4-O-5, β -1 and β -5 guaiacylpropane substructures, were recovered as major components from normal loblolly pine samples and as minor compounds from mutant samples (Table 3). In contrast, these mutant samples gave rise to unusual dimers **4-6** and **12-15**, provided with a C γ hydroxymethyl group. As the survival of this CH₂OH terminal group to the entire thioacidolysis-desulfurization procedure is only possible with -CH₂-CH₂-CH₂OH reduced side chains, these dimers are representative of lignin substructures comprising a DHCA unit. The mass spectra of their TMS derivatives displayed specific fragmentation patterns with losses of 90 amu (loss of TMSOH) and of 116 amu (loss of C₂H₄OTMS plus H) fragments. Not surprisingly, DHCA was incorporated into lignin only at its phenolic group or at its C-5 aromatic carbon.

Experiments with authentic 5-5' bisconiferaldehyde subjected to the whole thioacidolysis-desulfurization procedure revealed that the conjugated double bonds survived the Raney nickel reduction step to a very large extent (70%), probably due to the extended conjugated system (Jacquet, 1997). On this basis, unsaturated dimers **7-10** and **15** most likely originate from lignin substructures involving a coniferaldehyde unit. Dimers **10** and **15** are unique representatives of novel lignin substructures associating DHCA and coniferaldehyde. The recovery of such heterodimers diagnostic for the radical coupling of unusual lignin precursors further emphasizes the extent of the shortage in coniferyl alcohol. In addition to these unusual DHCA or unsaturated dimers, dimers with shortened C₆C₁ side chains (dimers **1**, **4**, **7** and **12**) were recovered in unusually high proportion from mutant pine samples (data not shown). These dimers may stem from lignin substructures provided with a vanillin end group or from the degradation of coniferaldehyde structures through reverse aldol condensation.

The quantitative evaluation of the lignin-derived dimers clearly showed the overwhelming importance of biphenyl bonds in the distribution of resistant linkages of the mutant lignin. Biphenyl dimers and, to a lesser extent, biphenyl ether dimers were recovered in relatively high amounts from mutant seedlings or mature trees (Table 3 and Figure 4). Conversely, β -5 and β -1 dimers were recovered in very low amounts from the mutant samples. The lignins of normal and mutant loblolly pines, therefore, have distinct patterns of interunit linkages. This difference is directly related to the incorporation of DHCA and coniferaldehyde units into the mutant lignins and to the radical coupling modes of these molecular species.

DISCUSSION

Previous characterization of lignin from CAD-deficient pine by NMR identified DHCA as a component of lignin. This finding came from the solution state NMR spectra of a milled wood lignin sample isolated from a single tree and with a 17% isolation yield. Furthermore, the genotype of the mature tree subjected to lignin isolation was simply inferred from CAD allozyme profiles of both its parents in addition to the brown-reddish coloration of its wood. Here, we studied several seedlings randomly selected from a larger population in which the genotype had been unambiguously determined by genetic finger-printing with RAPD markers (MacKay *et al.*, 1997). The evaluation of lignin structure was directly performed by thioacidolysis of the extract-free wood from pine seedlings and mature trees without any isolation step. Similar to other degradative methods, thioacidolysis does not afford the whole lignin polymer characterization, but only that of its labile fraction, which further emphasizes the necessity for combined physical and chemical approaches. However, the somehow limited

recovery yield of thioacidolysis monomers may be viewed not only as a limitation, but also as a structural information. In the present work, the lower thioacidolysis yield observed for the mutant, relative to the wild type samples, straightforwardly reflects the lignin structural alteration, namely the enrichment in resistant interunit bonds. In this study, we have demonstrated that the substantial incorporation of DHCA into lignins is specifically related to CAD deficiency in loblolly pine and linked, as is the brown wood color, to the *cad-nl* homozygous genotype. It is unlikely that DHCA would be formed from coniferyl alcohol as a post-polymerization modification because DHCA was involved in a high proportion of biphenyl 5-5 and biphenyl ether 4-O-5 linkages, untypical for coniferyl alcohol.

In agreement with recent literature evaluating lignin in plants displaying reduced CAD activity, this study further confirmed that a severe reduction in CAD activity induces dramatic changes in lignin structure while the lignin content is not altered to any great extent. High levels of coniferaldehyde and biphenyl interunit bonds were evidenced in lignin of the sorghum *bm6* mutant showing depressed CAD activity (Jacquet, 1997), similar to the CAD-deficient pine. In CAD down-regulated transgenic poplars, the extent to which the lignin structure was altered was related to the residual CAD activity. When CAD was moderately decreased, i.e., the residual activity was 30% of the wild type, the main structural change was an enrichment in free phenolic groups which proved beneficial to kraft pulping efficiency (Lapierre *et al.*, 1999). When CAD activity was more drastically reduced, i.e., to 3-8% of the wild type level, more dramatic alterations occurred, namely, the incorporation of sinapaldehyde units into the lignin together with a substantial enrichment in free phenolic groups and in carbon-carbon interunit resistant bonds (Lapierre *et al.*, unpublished data). Similarly, downregulation of CAD in transgenic tobacco to approximately 7% of wild type significantly increased the incorporation

of cinnamaldehyde groups (Halpin *et al.*, 1994). The incorporation of cinnamaldehyde into lignins seems therefore to be a common strategy employed by CAD-deficient pine, tobacco, sorghum, and poplar plants in order to maintain a lignin level compatible with their growth and development. In contrast, the massive incorporation of DHCA in addition to coniferaldehyde seems more specific of CAD-deficient pine. It is noteworthy that this building unit is systematically found in relatively small amounts in the lignins of normal gymnosperms (Gellerstedt *et al.*, 1984) while found as a trace component in angiosperm lignins (Lapierre, unpublished results). Thus, it seems possible to achieve different lignin profiles depending on the level of CAD activity and, perhaps, through different responses to low CAD activity in different taxa (e.g. poplar vs pine).

Important changes in the type of bonds within the lignin polymer accompanied the increased incorporation of coniferaldehyde and DHCA and the decreased utilization of coniferyl alcohol as lignin precursors. The altered bonding structure is evidenced by the frequency of biphenyl and biphenyl ether dimers being approximately tripled among thioacidolysis dimers in CAD-deficient pine. This shift is consistent with the fact that within the pool of lignin precursors there are far fewer reactive C_β available to form β -O-4 bonds as well as β -5 and β -1 linkages. Clearly, the C_β of DHCA is unreactive because the side chain lacks a double bond. The doubling of free phenolic hydroxyl groups in the lignins is most likely a consequence of the shift toward more C-C linkages and lower average molecular weight of the polymers. It is well established that β -O-4 bonds are the most labile of the lignin polymer and thus it is assumed that decreasing their abundance would have adverse effects on delignification during chemical pulping. However, the decrease in molecular weight and increase in free phenolic hydroxyl

groups may have the opposite effect on lignin removal. Indeed, data from recent pulping studies are now indicating that such a change in lignin structure may have some clear benefits. Increased lignin removal from CAD-deficient pine and poplar was observed in kraft and soda pulping, as well as in alkali treatment at room temperature (Baucher *et al.*, 1995; Lapierre *et al.*, 1999; Dimmel *et al.*, 1999; MacKay *et al.*, 1999). The common structural alteration of the pine and poplar lignins which can directly account for this phenomenon is their increased content in free phenolic groups associated with the CAD deficiency. Taken together, the data presented here point to significant opportunities to manipulate lignin subunit composition and structure with the potential for simplified pulping.

ACKNOWLEDGEMENTS

The authors received support for this work from the US Department of Agriculture, grant number 97-35103-4796.

REFERENCES

- Baucher, M.; Chabbert, B.; Pilate, G.; van Doorselaere, J.; Tollier, M.-T.; Petit-Conil, M.; Cornu, D.; Monties, B.; van Montagu, M.; Inzé, D.; Jouanin, L.; Boerjan, W. Red xylem and higher lignin extractability by down-regulating cinnamyl alcohol dehydrogenase in poplar (*Populus tremula* x *Populus alba*). *Plant Physiol.* **1996**, *112*, 1479- 1490
- Boudet A. M. A new view of lignification. *Trends in Plant Sci.* **1998**, *3*, 67-71.
- Dimmel, D. R.; MacKay, J. J.; Althen, E.; Parks, C.; Boon, J. J. Pulping, Bleaching, and Characterization of CAD-Deficient Wood. Intern. Symp. *Wood and Pulping Chem.* **1999**, Yokohama, Japan, June 7-10.

- Gellerstedt, G.; Lindfors, E.-V.; Lapierre, C.; Monties, B. Structural changes in lignin during kraft cooking. *Svensk Papperstidn.* **1984**, 87, R61-R67.
- Halpin, C.; Knight, M. E.; Foxon, G. A.; Campbell, M. M.; Boudet, A. M.; Boon, J. J.; Chabbert, B.; Tollier, M.-T.; Schuch, W. Manipulation of lignin quality by downregulation of cinnamyl alcohol dehydrogenase. *Plant J.* **1994**, 6, 339- 350.
- Hibino, T.; Takabe, J.; Kawazu, T.; Shibata, D.; Higuchi, T. Increase of cinnamaldehyde groups in lignin of transgenic tobacco plants carrying an antisense gene for cinnamyl alcohol dehydrogenase. *Biosci. Biotech. Biochem.* **1995**, 59, 929-931.
- Jacquet G. Structure et réactivité des lignines de graminées et acides phénoliques associés: développement des méthodologies d'investigation. *PhD Thesis* **1997**, Université Aix-Marseille III, 181 p.
- Jacquet, G.; Pollet, B.; Lapierre, C.; Mhamdi, F.; Rolando, C. New ether-linked ferulic acid-coniferyl alcohol dimers identified in grass straws. *J. Agr. Food Chem.* **1995**, 43, 2746-2751.
- Lapierre, C. Application of new methods for the investigation of lignin structure. In *Forage Cell Wall Structure and Digestibility*. Jung, H.G., Buxton, D.R., Hatfield, R.D., Ralph, J. Eds; American Society of Agronomy: Madison, WI, USA, **1993**, pp. 133-166.
- Lapierre, C.; Pollet, B.; Rolando, C. New insights into the molecular architecture of hardwood lignins by chemical degradative methods. *Res. Chem. Intermed.* **1995**, 21, 397-412.
- Lapierre, C.; Pollet, B.; Petit-Conil, M.; Toval, G.; Romero, J.; Pilate, G.; Leplé, J.-C.; Boerjan, W.; Ferret, V.; De Nadai, V.; Jouanin, L. Structural alteration in transgenic poplars with depressed cinnamyl alcohol dehydrogenase or caffeic acid O-methyltransferase

- activity have an opposite impact on the efficiency of industrial kraft pulping. *Plant Physiol.* **1999**, *119*, 153-163.
- Lapierre, C.; Tollier, M. T.; Monties, B. A new type of constitutive unit in lignins from the corn bm3 mutant. *C. R. Acad. Sci. Ser. 3.* **1988**, *307*, 723-728.
- MacKay, J. J.; O'Malley, D. M.; Presnell, T.; Booker, F. L.; Campbell, M. M.; Whetten, R. W.; Sederoff, R.R. Inheritance, gene expression and lignin characterization in a mutant pine deficient in cinnamyl alcohol dehydrogenase. *Proc. Natl. Acad. Sci. USA.* **1997**, *94*, 8255-8260.
- MacKay, J.; Presnell, T.; Jameel, H.; Taneda, H.; O'Malley, D.; Sederoff, R. R. Modified lignin and delignification with a mutant loblolly pine. *Holzforschung.* **1999**, *53*, 403-410.
- Ralph, J.; Hatfield, R. D.; Piquemal, J.; Yahiaoui, N.; Pean, M.; Lapierre, C.; Grima-Pettenati, J.; Boudet, A. M. NMR characterization of altered lignins extracted from tobacco plants down-regulated for lignification enzymes cinnamyl-alcohol dehydrogenase and cinnamoyl-CoA reductase. *Proc. Nat. Acad. Sci.* **1998**, *95*, 12803-12808.
- Ralph, J.; Hatfield, R.; Quideau, S.; Helm, R. F.; Grabber, J. H.; Jung, H.-J.G. Pathway of p-coumaric incorporation into Maize lignin as revealed by NMR. *J. Am. Chem. Soc.* **1994**, *116*, 9448-9456.
- Ralph, J.; MacKay, J. J.; Hatfield, R. D.; O'Malley, D. M.; Whetten, R. W.; Sederoff, R. R. Abnormal lignin in a loblolly pine mutant. *Science.* **1997**, *277*, 235-239.
- Sederoff, R. R.; MacKay, J. J.; Ralph, J.; Hatfield, R. D. Unexpected variation in lignin. *Curr. Opin. In Plant. Biol.* **1999**, *2*, 145-152.

- van Doorsselaere, J.; Baucher, M.; Chognot, E.; Chabbert, B.; Tollier, M.-T.; Petit-Conil, M.; Leplé, J.-C.; Pilate, G.; Cornu, D.; Monties, B.; Van Montagu, M.; Inzé, D.; Boerjan, W.; Jouanin, L. A novel lignin in poplar trees with reduced caffeic acid/5-hydroxyferulic acid O-methyltransferase activity. *Plant J.* **1995**, 8, 855-864.
- Whetten, R. W.; Mackay, J. J.; Sederoff, R. R. Recent advances in lignin biosynthesis. *Ann. Rev. Plant Physiol. Plant Molec. Biol.* **1998**, 49, 585-609.

Figure 1. Inheritance of the *cad-n1* allele and genetic control of altered lignin. Inheritance of the *cad-n1* allele was followed in a selfed family from a parent tree, which was heterozygous *cad-n1*. The *cad* genotype of several progeny was determined by genetic finger-printing in the region of the *cad* gene locus, by using RAPD (randomly amplified polymorphic DNAs) markers (MacKay et al., 1997). The three genotypes illustrated above segregated in a 1:2:1 ratio, consistent with Mendelian expectations. Only homozygous *cad-n1* seedlings had brown-reddish wood, linking the altered color (and lignin) with that specific genotype. Several homozygous wild type (*Cad/Cad*) and homozygous *cad-n1* (*cad-n1/cad-n1*) seedlings were selected, for lignin determination and further analyzed by thioacidolysis.

Figure 2. Importance (% molar) of various thioacidolysis monomers relative to the guaiacyl G-CHR-CHR-CH₂R major isomers (R=SEt) released from mutant and wild type extract-free pine woods.

Figure 3. Main dimers recovered from mutant and wild type pine samples. R = H in 11, 14, 17 and 22; R = CH₃ in 12, 15, 18 and 23; R = C₂H₅ in 13, 16, 19 and 24. R = -CH₂-CH₂OH in 20. Dimers with CH₂OH at C or with unsaturated side chains originate only from mutant samples.

Figure 4. Relative frequency (% molar) of the main thioacidolysis dimers (Figure 3) recovered from normal and mutant pine seedlings and mature trees. These dimers are representative of the lignin condensed bonding patterns.

Table 1. Yield in Lignin-derived Thioacidolysis Monomers Recovered from Wild Type and Mutant Loblolly Pine Extract-free Wood Samples. Results are expressed in μ moles per gram of Klason Lignin or in percentage of units (per 100 C₆C₃) only involved in β -O-4 Bonds (values between brackets).


10-month-old seedlings	
Wild type	Mutant
S ₁₁ : 1080 (24.3%)	S ₃ : 329 (7.4%)
S ₂₁ : 1076 (24.2%)	S ₅ : 298 (6.7%)
S ₁₁₇ : 1111 (25.0%)	S ₁₅₂ : 289 (6.5%)
S ₁₃₈ : 973 (21.9%)	S ₁₆₀ : 280 (6.3%)
S ₁₃₉ : 1062 (23.9%)	
Mean value : 1060 \pm 60	Mean value : 299 \pm 21
Mature trees	
Wild type	Mutant
	2-year-old : 360 (8.1%)
12-year-old: 991 (22.3)%	12-year-old: 373 (8.4%)

Table 2. Molar Ratio H/G of *p*-hydroxyphenyl H Monomers H-CHR-CHR-CH₂R Relative to Analogous Guaiacyl G-CHR-CHR-CH₂R Isomers Released from Wild Type and Mutant Samples (S = 10-month-old Seedlings).

Wild type	Mutant
S ₁₁ : 0.029	S ₃ : 0.047
S ₂₁ : 0.015	S ₅ : 0.184
S ₁₁₇ : 0.008	S ₁₅₂ : 0.058
S ₁₃₈ : 0.009	S ₁₆₀ : 0.067
S ₁₃₉ : 0.019	2-year-old : 0.275
12-year-old : 0.033	12-year-old: 0.11

Table 3. Main Dimers (Figure 3) Recovered from Wild Type or Mutant Pine Seedlings (10-month-old S) or Mature Tree. Results are expressed in μ moles per gram of Klason lignin.

Pine	Wild type			Mutant		
Dimer and Sample	S138	S139	12-year-old	S 152	S160	12-year-old
<i>1-3</i> biphenyl	51.5	48.8	47.9	22.6	25.4	43.5
DHCA biphenyl <i>4-6</i>	-	-	-	43.1	51.6	81.5
Unsaturated biphenyl <i>9-10</i>	-	-	-	19.1	16.2	22.7
<i>11</i> biphenyl ether	11.5	13.8	14	3.1	2.7	5.8
DHCA biphenyl ether <i>12-14</i>	-	-	-	13.4	19.1	29.8
Unsaturated biphenyl ether <i>15</i>	-	-	-	5.1	5.1	7.4
β -1 <i>16</i>	48.2	58.9	56.1	5.4	4.7	6.3
β -5 <i>17</i>	51	71.6	65.9	5.5	6.3	7.3
Total dimers	162	193	184	117	131	204



* *Cad*: normal *cad* gene; *cad-n1*: mutant *cad* gene

Figure 1




Figure 2




Figure 3




Figure 4

